įĮ.
M
ij.
l.I
Land
- Şur
ŭ;
II.

IN THE UNITED STATES PATE	INT AND TRADEMARK	COFFICE /
In re Application of)	# Yll
Christian Kunert et al. Serial No.) Group:	Ru andt A
Filed: Title: COATING OF COOLED DEVICES) Examiner:	1-18-02

PRELIMINARY AMENDMENT

Assistant Commissioner of Patents Washington, DC 20231

Sir:

Prior to calculating the filing fee, please enter the following amendments to the application.

IN THE CLAIMS

Please amend the following claims:

In claim 3, line 1, delete "or 2".

In claim 4, line 1, delete "one of claims 1 to 3" and substitute therefor --claim 1--.

In claim 6, line 1, delete "one of claims 1 to 5" and substitute therefor --claim 1--.

In claim 7, line 1, delete "one of claims 1 to 6" and substitute therefor --claim 1--.

In claim 8, line 1, delete "one of claims 1 to 6" and substitute therefor --claim 1--.

In claim 9, line 1, delete "one of claims 1 to 6" and substitute therefor --claim 1--.

Please add the following new claims:

- --10. Structural component according to claim 2, characterized in that the plastic is halogen-containing.
- 11. Structural component according to claim 2, characterized in that the coating thickness is less than 1 mm.
- 12. Structural component according to claim 3, characterized in that the coating thickness is less than 1 mm.
- 13. Structural component according to claim 2, characterized in that the base body consists of copper, platinum, steel or aluminum, or of alloys of these metals.
- 14. Structural component according to claim 3, characterized in that the base body consists of copper, platinum, steel or aluminum, or of alloys of these metals.
- 15. Structural component according to claim 4, characterized in that the base body consists of copper, platinum, steel or aluminum, or of alloys of these metals.
- 16. Structural component according to claim 5, characterized in that the base body consists of copper, platinum, steel or aluminum, or of alloys of these metals.
- 17. Structural component according to claim 2, characterized in that it is an agitator for the homogenization of melts.